

Grade-Thickness Interval	Number of Trenches in Grade-Thickness Interval	Thickness of Mineralized Zone			U ₃ O ₈ (ppm)	V ₂ O ₅ (ppm)
		Minimum (m)	Maximum (m)	Average (m)		
GxT 50 - 100	123	0.2	1.4	0.74	109	805
GxT 100 - 250	120	0.1	2.4	0.83	249	976
GxT 250 - 1400	42	0.2	2.7	1.00	630	1156
Total Area GxT >50	285	0.1	2.7	0.82	201	881