

## Assay Results for Aricheng C

Bore Hole Number	Intercept				Grade	
	From (m)	To (m)	Interval (m)	Estimated True Thickness (m)	U <sub>3</sub> O <sub>8</sub> (%)	U <sub>3</sub> O <sub>8</sub> (lbs/st)
ARC-001	46.0	50.0	4.0	3.4	0.109	2.2
	57.0	64.0	7.0	5.9	0.092	1.8
	70.0	78.0	8.0	6.8	0.078	1.6
	129.0	135.0	6.0	5.1	0.040	0.8
	142.0	155.0	13.0	11.0	0.098	2.0
	212.0	214.0	2.0	1.7	0.062	1.2
ARC-002	140.0	145.0	5.0	4.2	0.059	1.2
	174.0	179.0	5.0	4.2	0.097	1.9
	216.0	217.0	1.0	0.8	0.118	2.4
ARC-003 Including Including	203.0	212.0	9.0	7.6	0.128	2.6
	258.0	286.0	28.0	23.7	0.099	2.0
	259.0	270.0	11.0	9.3	0.137	2.7
	281.0	286.0	5.0	4.2	0.131	2.6
ARC-004	58.0	64.0	6.0	5.1	0.111	2.2
	79.0	83.0	4.0	3.4	0.069	1.4
	109.0	152.0	43.0	36.5	0.092	1.8
	179.0	182.0	3.0	2.5	0.110	2.2
	211.0	219.0	8.0	6.8	0.055	1.1